


ABSTRACT

The antistatic agent for resins of the present invention contains phosphonium salts represented by the general formula (1) below:



- 5 (wherein R^1 , R^2 , and R^3 are each a straight-chain or branched alkyl group having 3 to 8 carbon atoms, and R^4 is a straight-chain or branched alkyl group having 10 to 22 carbon atoms; each alkyl group may have substituted hydroxy group or alkoxy group; R^1 , R^2 , and R^3 may be the same or different from each another; and X^- is a tetrafluoroborate ion or
- 10 a hexafluorophosphate ion).